



## ZINSSER® ALLCOAT EXTERIOR MATT

# Outdoor paint provides ultimate performance on all surfaces

- Excellent colour retention
- Weather resistant
- Can be applied to different types of surfaces
- Flexible coating
- Recoatable in 1 hour

# ZINSSER® ALLCOAT EXTERIOR MATT

## POPIS PRODUKTU (DLOUHÝ)

Developed for the durable decoration of wood, metal, masonry, plastic, concrete and façade cladding. Self-priming, sanding is unnecessary. Protects dry coating against contamination by mould. ALLCOAT® Exterior Matt is not a rust inhibitive product, apply only on previously protected metal.

## DOPORUČENÉ POUŽITÍ

Developed for all outside surfaces, ALLCOAT® Exterior Matt is ideal for use on wood, plastic, galvanised metal, steel, façade cladding, weathered bitumen, plaster, brick, stone, concrete, and more. ALLCOAT® Exterior Matt can be used as a primer and adheres directly on existing glossy coatings without the need for sanding. A separate primer is unnecessary for most applications. ALLCOAT® Exterior Matt provides superb resistance to cracking, blistering, flaking, rain, and severe weather conditions.

Two-layer system: The first layer of ALLCOAT® Exterior Matt works as a primer and seals the surface. The top layer completes the sealing process. Where necessary, apply Zinsser B-I-N® to bleeding knots and resin streaks. For new or unpainted cedar, redwood, or other resinous timbers prime with Zinsser Cover Stain®

## TECHNICAL\_DATA

Hustota (g/cm <sup>3</sup> ):	1,25
Úroveň lesku:	Matt
Úroveň lesku při 60°:	± 2%
Úroveň lesku při 85°:	± 3%
Obsah pevných látek v hmotnosti:	40%
Obsah pevných látek v objemu:	40%
Propustnost pro vodní páru:	Sd = 0,44 m (V2 EN ISO 7783)

## DRY\_TIMES\_BY\_20

Suché na manipulaci:	1 h
Suchý nátěr:	1 h
Plně vytvrzené:	7 days

## DOPORUČENÁ TLOUŠŤKA MOKRÉHO FILMU

100 µm/coat

## DOPORUČENÁ TLOUŠŤKA SUCHÉHO FILMU

40 µm/coat

## TEORETICKÁ SPOTŘEBA

8 - 12 m<sup>2</sup>/l/coat

## PRAKTICKÁ SPOTŘEBA

Practical coverage depends on many factors such as porosity and roughness of the substrate. On porous surfaces coverage will be reduced e.g. sawn timber - 4-8 m<sup>2</sup> per litre. A normal application consists of two layers. Apply an extra layer to areas with high exposure such as window sills and eaves.

## PŘÍPRAVA POVRCHU

The surface must be clean, dry and free of dust, dirt, grease, oil, wax, mould, glue residues, etc. Remove old non-adhering layers of paint. Clean the surface using Rust-Oleum ND14. Use Mathys AMW concentrate to remove algae and mould.

## NÁVOD K POUŽITÍ

Mix carefully before use.

## PODMÍNKY POUŽITÍ

10°C-32°C, < 85% R.H.

## APLIKACE A REDENÍ: STETEC

Apply with brush with synthetic bristle

## APLIKACE A ŘEDĚNÍ: VÁLEČEK

Apply with synthetic roller

## APLIKACE A ŘEDĚNÍ: BEZVZDUCHOVÝ SPREJ

Nozzle: 0.017 / Pressure: 140 - 170 bar

## ČIŠTĚNÍ ZAŘÍZENÍ / ROZLITÍ

Use lukewarm soapy water to clean off stains and materials.

## POZNÁMKY

ALLCOAT® Exterior Matt is not recommended for use on floors, terraces, or horizontal surfaces that may be drenched in water or exposed to water for a long period of time. Before applying ALLCOAT® Exterior Matt, we recommend that you thoroughly sand and degrease unweathered/new powder coatings and similar surfaces. Not suitable for application onto newplastisol or a new powder coating. These surfaces must be fully weathered. Not suitable onto PVDF cladding : apply Rust-Oleum PVDF Primer first. ALLCOAT® Exterior Satin has no anti corrosive properties, so apply Zinsser® 1-2-3 on bare ferrous metal surfaces. Onto rusty surfaces, prime with Rust-Oleum® Peganox® or CombiColor® Aqua Primer.

## DATA\_SAFETY\_DATA

Úroveň těžkých organických

látek:	35 g/l
Kategorie VOC:	A/d
Limitní hodnota VOC:	130 g/l (2010)
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety Information printed on the can.

## DOBA POUŽITELNOSTI

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5 and 35°C.

last\_updated: 20/12/2024

footer\_data\_colors\_pack\_sizes: footer\_data\_colors\_pack\_sizes.value

footer\_data\_disclaimer: footer\_data\_disclaimer.value

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM s-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
info@rust-oleum.eu