



ZINSSER® ALLCOAT EXTERIOR MATT

Outdoor paint provides ultimate performance on all surfaces

- Excellent colour retention
- Weather resistant
- Can be applied to different types of surfaces
- Flexible coating
- Recoatable in 1 hour



ZINSSER® ALLCOAT EXTERIOR MATT

POPIS PRODUKTU (DLHY)

Developed for the durable decoration of wood, metal, masonry, plastic, concrete and façade cladding. Self-priming, sanding is unnecessary. Protects dry coating against contamination by mould. ALLCOAT® Exterior Matt is not a rust inhibitive product, apply only on previously protected metal.

ODPORÚČANÉ POUŽITIE

Developed for all outside surfaces, ALLCOAT® Exterior Matt is ideal for use on wood, plastic, galvanised metal, steel, façade cladding, weathered bitumen, plaster, brick, stone, concrete, and more. ALLCOAT® Exterior Matt can be used as a primer and adheres directly on existing glossy coatings without the need for sanding. A separate primer is unnecessary for most applications. ALLCOAT® Exterior Matt provides superb resistance to cracking, blistering, flaking, rain, and severe weather conditions.

Two-layer system: The first layer of ALLCOAT® Exterior Matt works as a primer and seals the surface. The top layer completes the sealing process. Where necessary, apply Zinsser B-I-N® to bleeding knots and resin streaks. For new or unpainted cedar, redwood, or other resinous timbers prime with Zinsser Cover Stain®

TECHNICAL DATA

Hustota (g/cm ³):	1,25
Úroveň lesku:	Matt
Úroveň lesku pri 60°:	± 2%
Úroveň lesku pri 85°:	± 3%
Obsah pevných látok v hmotnosti:	40%
Obsah pevných látok v objeme:	40%
Priepustnosť vodnej pary:	Sd = 0,44 m (V2 EN ISO 7783)

DRY TIMES BY 20

Suché na manipuláciu:	1 h
Suchý na opätovné natieranie:	1 h
Úplne vytvrdené:	7 days

ODPORÚČANÁ HRúbKA MOKRÉHO FILMU

100 µm/coat

ODPORÚČANÁ HRúbKA SUCHÉHO FILMU

40 µm/coat

TEORETICKÁ SPOTREBA

8 - 12 m²/l/coat

PRAKTICKÁ VÝDATNOSŤ

Practical coverage depends on many factors such as porosity and roughness of the substrate. On porous surfaces coverage will be reduced e.g. sawn timber - 4-8 m² per litre. A normal application consists of two layers. Apply an extra layer to areas with high exposure such as window sills and eaves.

PRÍPRAVA POVRCHU

The surface must be clean, dry and free of dust, dirt, grease, oil, wax, mould, glue residues, etc. Remove old non-adhering layers of paint. Clean the surface using Rust-Oleum ND14. Use Mathys AMW concentrate to remove algae and mould.

NÁVOD NA POUŽITIE

Mix carefully before use.

PODMIENKY APLIKÁCIE

10°C-32°C, < 85% R.H.

APLIKÁCIA A RIEDENIE: STETEC

Apply with brush with synthetic bristle

APLIKÁCIA A RIEDENIE: VALEC

Apply with synthetic roller

APLIKÁCIA A RIEDENIE: BEZVZDUCHOVÉ STRIEKANIE

Nozzle: 0.017 / Pressure: 140 - 170 bar

ČISTENIE ZARIADENIA / POSTRIEKANIE

Use lukewarm soapy water to clean off stains and materials.

POZNÁMKY

ALLCOAT® Exterior Matt is not recommended for use on floors, terraces, or horizontal surfaces that may be drenched in water or exposed to water for a long period of time. Before applying ALLCOAT® Exterior Matt, we recommend that you thoroughly sand and degrease unweathered/new powder coatings and similar surfaces. Not suitable for application onto newplastisol or a new powder coating. These surfaces must be fully weathered. Not suitable onto PVDF cladding : apply Rust-Oleum PVDF Primer first. ALLCOAT® Exterior Satin has no anti corrosive properties, so apply Zinsser® 1-2-3 on bare ferrous metal surfaces. Onto rusty surfaces, prime with Rust-Oleum® Peganox® or CombiColor® Aqua Primer.

DATA SAFETY DATA

Úroveň VOC:	35 g/l
Kategória VOC:	A/d
Limit VOC:	130 g/l (2010)
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety Information printed on the can.

SKLADOVATELNOSŤ

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5 and 35°C.

last_updated: 20/12/2024

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM s-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu