



## ZINSSER<sup>®</sup> BULLS EYE 1-2-3

# Stain blocking sealer & adhesion primer

- Seals stains of graffiti, grease, rust, cedar & redwood tannin
- Rust inhibitive coating, ideal for new metal
- Adheres to most surfaces without pre-sanding or deglossing
- Fast drying
- White and pastel shades

# ZINSSER® BULLS EYE 1-2-3

## BESKRIVELSE

Universal acrylic water based stain blocking sealer and adhesion primer.

## ANBEFALT BRUK

Product can be applied on interior and exterior walls, ceilings, doors, trim, foundations, railings, and related paintable surfaces. Bulls Eye 1-2-3 adheres on wood, plaster, concrete, gloss enamels, hardboard, glass and tiles. The product provides a rust inhibitive coating on iron railings, steel frames, piping, etc. Resists the growth of mould and mildew on dried film in damp, humid environments. Resistant to high pH surfaces (up to 12,5) including; plaster, poured concrete, concrete block and stucco. Seals porous surfaces and traps most stains in the primer film (graffiti, grease, rust, cedar & redwood tannin, creosote and asphalt stains). Some stains may require a second coat.

Interior Substrates: new or previously painted drywall, cured plaster, cement, poured concrete, concrete block, stucco, wood (pine, fir, birch, oak and plywood), aluminum, iron, steel and galvanized metal, PVC, glossy laminates and other interior surfaces.

Exterior Substrates: recommended for all types of wood (new or previously painted pine, cedar, redwood, plywood and pressure treated wood), hardboard, metal (aluminium, steel, iron and galvanized metal), PVC, fiberglass, masonry (stucco, concrete block, poured concrete and brick).

## TEKNISKE DATA

Tetthet:	1,26
Glansgrad:	Satinert
Glansgrad ved 60°:	Satin: 23%
Tørrstoffinnhold i vekt:	50,5%
Tørrstoffinnhold i volum:	34%

## TØRKETID VED 20°C/50% RELATIV LUFTFUKTIGHET

Støvtør:	30 minutes
Overmalbar:	1 h
Herdetid:	7 days

## ANBEFALT VÅTFILMTYKKELSE

80 - 110 µm

## ANBEFALT TØRRFILMTYKKELSE

30 - 40 µm

## TEORETISK FORBRUK

9 - 12 m<sup>2</sup>/l

## PRAKTISK FORBRUK

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## KLARGJØRING AV OVERFLATE

Surfaces should be clean, dry, sound and free of dust, dirt, excessive chalky material, grime, grease, oil, wax, mildew, wallpaper adhesive or any contamination that may interfere with adhesion. If unsure, always wash surface with a household ammonia and water solution, or an appropriate cleaning solution. Remove any unsoundly adhered coatings. Sand any remaining paint film edges smooth with the surface. Lightly sand exposed exterior wood with 80 to 100 grit sandpaper to remove loose or weathered wood fibres. Attempt to remove existing stains by washing, sanding, scraping, etc.

Kill mildew with a suitable mildew Killer such as Rust-Oleum FK 111.

Remove rust and clean metal and new galvanized substrates with a suitable cleaner such as Rust-Oleum ND14. On wood first spot prime knots with Zinsser® B-I-N Primer-Sealer before priming full surface with Bulls Eye 1-2-3.

## RIKSAVVISNING

**Tilgjengelige farger & størrelse på forpakninger:** Vennligst referer til den respektive produktsiden på [www.rust-oleum.eu](http://www.rust-oleum.eu) for en oversikt over tilgjengelige farger og størrelse på forpakninger.

**Ansvarsfraskrivelse:** Så langt vi kjenner til er informasjonen i dette dokumentet korrekt og nøyaktig. Den er gitt i god tro, men uten garanti. Brukeren må selv avgjøre om våre produkter er egnet for hans/hennes bestemte formål. Ikke under noen omstendigheter skal Rust-Oleum Europe bli gjort ansvarlig for indirekte eller tilfældige skader. Produktene må lagres, håndteres og påføres under forhold som tilfredsstiller Rust-Oleum Europes anbefalinger som er detaljert beskrevet i den siste oppdaterte kopien av produktdatabladet. Brukerne er selv ansvarlige for at de har den siste oppdaterte kopien. De siste oppdaterte kopier av produktdatabladet er tilgjengelig, og kan lastes ned gratis fra [www.rust-oleum.eu](http://www.rust-oleum.eu), eller de kan fås ved forespørsel til vår kundeserviceavdeling. Rust-Oleum Europe forbeholder seg retten til å endre egenskapene til produktene sine uten forhåndsvarsel.

Rust-Oleum Netherlands B.V.  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
info@rust-oleum.eu

Rust-Oleum France S.A.S.  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
info@rust-oleum.eu

N.V. Martin Mathys S.A.  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
info@rust-oleum.eu

## FORBEREDELSE

Stir thoroughly before and during application.

## PÅFØRINGSBETINGELSER

Apply when air and surface temperature is between 10 and 32°C and relative humidity is between 10 and 70%. Substrate moisture content should not exceed 12%.

## PÅFØRING & FORTYNNING: PENSEL

Use nylon, polyester or synthetic brush. Do not dilute.

## PÅFØRING & FORTYNNING: RULLE

Use nylon, polyester or synthetic roller. Do not dilute.

## PÅFØRING & FORTYNNING: LUFTFRI SPRØYTE

Tip size: 0,015 - 0,017 inch. Fluid pressure: 140 - 175 bar. Do not dilute.

## PÅFØRING & FORTYNNING: FORSTØVNINGSSPRØYTE

Dilute with max 10% water. Atomizing pressure: 2 - 4 bar.

## RENGJØRING AV UTSTYR/SPILL

(Warm) water. If dried on tools, let soak overnight in a 1:4 ammonia and water solution.

## MERKNADER

Bulls Eye 1-2-3 is not intended for blocking heavy water-stains or for application to floors, decks, roof surfaces or any surface subject to immersion or prolonged contact with water.

Bulls Eye® 1-2-3 can be tinted with max. 16 ml of universal color paste per liter.

## SIKKERHETSDATA

VOC nivå:	4 g/l
VOC ferdigblandet:	4 g/l
VOC kategori:	A/g
VOC grense:	30 g/l
Merknader angående sikkerhet:	Consult Safety Data Sheet and Safety Information printed on the can.

## HOLDBARHET

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5 and 35°C

Utstedt dato: 10/06/2024